

## TECHNICAL DATA SHEET P101 2 PACK ANTI-GRAFFITI COATING

TDS: CVP1011A  
205/P101/1

### DESCRIPTION:

Coo-Var P101 is a two pack, clear aliphatic polyurethane coating which provides a highly graffiti-resistant finish inside or outside with B.S. Flame Spread Rating.

### RECOMMENDED USE:

Coo-Var P101 is used in areas of high hygiene, chemical contact and surfaces subject to graffiti attack. Is ideal for bridges, statues, walls, toilets and more. Can be used over compatible water based paints to provide a glaze over a colour. Not for use over conventional solvent based paints.

### AVAILABILITY:

1 litre and 5 litre mixed packs

### FINISH:

Gloss

### COLOUR:

Clear

### TYPICAL S.G. (SPECIFIC GRAVITY):

1.07 @ 20 °C

### VOLUME SOLIDS:

47%

### WET FILM THICKNESS W.F.T

120 to 135 microns

### DRY FILM THICKNESS D.F.T

65 to 75 microns

### EXPECTED SPREADING RATE:

35 to 40 sq.m / 5 kilo pack  
@ 75 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

### TYPICAL VISCOSITY:

N/A

### FLASH POINT:

40 °C (closed cup)

### CURE TIME: @ RECOMMENDED D.F.T

Initial cure: 3 to 4 hours @ 20 °C

Hard dry: 16 to 24 hours @ 20 °C

Full cure: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, curing and performance of any coating.

### POTLIFE:

6 to 8 hours @ 20 °C

**Pot Life - Once the parts are mixed together the material has to be used within the time stated.**

### MINIMUM OVERCOATING TIME:

Minimum 16 hours

### APPLICATION SPECIAL CONDITIONS:

See Application Conditions.

### VOC CONTENT:

Max 498 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

### APPLICATION DETAILS:

Application See Application Conditions.  
restrictions

Method: Brush or short nap mohair roller. Airless Spray

Thinner Do Not Thin. Do Not Thin.  
(Max vol):

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

Ellenshaw Works  
Lockwood Street, Hull HU2 0HN  
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR  
Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)  
[www.coo-var.co.uk](http://www.coo-var.co.uk)

**P101 2 PACK ANTI-GRAFFITI COATING**

**205/P101/1**

Nozzle size: N/A

Nozzle pressure: 1800 to 2000 psi

Cleaning solvent: Anti-Graffiti Brushwash

Recoat interval: Minimum 16 hours Maximum 72 hours

**SURFACE PREPARATION:**

All surfaces should be laitance free, clean, dry, sound and free from contaminants.

**MIXING INSTRUCTIONS:**

The product is supplied in two containers: one larger than the other and labelled Base. The other smaller one labelled Hardener. The contents of the pack marked Hardener are added to the contents of the larger pack marked Base and thoroughly mixed together, preferably by slow speed electric mixer for 2 minutes or until thoroughly mixed. Failure to mix the material correctly will lead to uncured areas in the coating.

**APPLICATION CONDITIONS:**

Apply 5 to 30°C by brush or short nap mohair roller. This product can also be spray applied in approved conditions. When brush or roller applied at ambient temperatures - these products do not emit free Isocyanate at above levels recommended by C.O.S.H.H. Regulations. However, the protective measures shown on the product labels and safety data sheets must be followed. When used at elevated temperatures or atomised (sprayed) these products do emit small amounts of free Isocyanate and should only be sprayed in an atmosphere controlled working area, with suitable ventilation or flame proof extraction of air. Operatives must wear suitable protective clothing and separate air fed breathing apparatus. It is recommended that spraying of these products be avoided wherever possible to facilitate uncomplicated application and site conditions.

**PRECEDING COAT:**

Apply direct. Prime porous concrete, plaster and brickwork with Coo-Var High Performance Primer. Asphalt can only be coated if primer is used first.

**SUBSEQUENT COAT:**

Coo-Var P101 2 Pack Anti-Graffiti Coating.

**REMARKS:**

Not for use over conventional solvent based paints.

**HEALTH AND SAFETY:**

For hardener see safety data sheet - SDS 10751. For base see safety data sheet - SDS 10752.

**ISSUED:**

07 July 2014

**REVISION:**

2

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

**Ellenshaw Works**  
**Lockwood Street, Hull HU2 0HN**  
**Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266**

**COO-VAR**  
**Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)**  
**[www.coo-var.co.uk](http://www.coo-var.co.uk)**