




PRODUCT DESCRIPTION & USE

Armstead Trade Vinyl Matt is a professional quality matt emulsion that minimises surface imperfections. Suitable for all normal interior and ceiling surfaces. Particularly suited for large job applications in commercial, institutional and industrial structures.

KEY BENEFITS

- Good opacity
- Minimises surface imperfections
- For interior walls & ceilings

PACK SIZES



COLOUR RANGE

Armstead Trade Exclusive: 150 colours
 BS4800: 100 colours
 RAL: 45 colours
 NCS 1 & 2: 3487 colours
 Visit www.armsteadtrade.co.uk

FILM PROPERTIES

Chemical Resistance: Not suitable.

Heat Resistance: Not suitable for use on heated surfaces e.g. radiators.

Water Resistance: Will tolerate the levels of atmospheric humidity present in normal interior environments.

COMPOSITION (NOMINAL)

Pigment: Lightfast Pigments.
 Binder: Acrylic Copolymer Emulsion.
 Solvent: Water.

VOLUME SOLIDS

35% (nominal) for Brilliant White, colours will vary.

SURFACE PREPARATION

Surfaces must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease and salts. New plaster and masonry must be fully dry before priming. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding.

APPLICATION



Brush, roller, & airless spray.

As with other water-based paints, do not apply in temperatures below 8°C (as recommended by British Standard BS 6150)

SYSTEM INFORMATION

Stir thoroughly before use. On very absorbent surfaces apply a sealing coat of thinned Armstead Trade Vinyl Matt. Finishing: Apply 1 or 2 coats of Armstead Trade Vinyl Matt.

Note: Special precautions should be taken during surface preparation of pre-1990s paint surfaces over wood and metal as they may contain harmful lead.

PRACTICAL COVERAGE



A guide to the practical coverage which can be achieved under normal conditions is up to 14m²/litre.

THINNING

Sealing new/bare surfaces: Add up to 1 part clean water to 10 parts paint.

Normal use: Thinning is not required.

Airless spray application: For normal use thin up to 10% (1 part water to 10 parts paint)

SPRAY RECOMMENDATIONS

Airless Spray: For best results use a 515 or 517 Low Pressure tip @1300 – 1700 psi (89 – 117 bar). Alternatively, use a 517 tip @ 2000 – 2400 psi (138 – 165 bar). *Please note that the above recommendations are intended as a guideline only and some adjustments may need to be made to accommodate equipment type & age, substrate type and individual site & atmospheric conditions.*

DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



Touch Dry: 1-2 hours*
Recoat: 2-4 hours*

*Dependent upon temperature and humidity.

CLEANING UP



After use, remove as much paint as possible from equipment before cleaning with clean water.

TRANSPORTATION & STORAGE

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat.: A/a) : 30g/l (2010) This product contains max. 1g/l VOC

VOC Content Trace * 0-0.1% (*Low for dark colours)
 VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

FURTHER SUPPORT

Online: www.armsteadtrade.co.uk
Email: armstead.advice@akzonobel.com
Phone: 0333-222-70-70



Like us on Facebook



Videos on YouTube



Follow us on Twitter



Let's create together a better future for our planet. Find out how at:

www.armsteadtrade.co.uk/sustainability

AkzoNobel, the AkzoNobel logo, Armstead, trademarks of the
AkzoNobel group © AkzoNobel 2023