

BLACKFRIAR PAINTS LTD

TECHNICAL DATA SHEET

BF037 **Blackfriar Priming Paint (Wood Aluminium).**

Review date:
08/01/2007

<u>Product Information</u>	<u>Technical Spec</u>	<u>Thinning</u>
<u>Description</u>	<u>Composition</u>	Up to 10% with white spirit
An aluminium primer for hardwoods.	A blend of alkyd resins and oils with leafing aluminium and titanium dioxide.	<u>Drying Time</u>
<u>Usage/purpose</u>	<u>Properties</u>	Touch dry in 2-4 hours Recoatable after 16 hours under normal conditions (20°C 50% r/h).
Specifically formulated for painting new or old bare hard or resinous woods.	VOC Content: 259 g/litre.	<u>Cleaning</u>
<u>Characteristics</u>	<u>Performance</u>	Clean application equipment or spills with white spirit or Blackfriar Brush Cleaner.
An aluminium shade liquid primer with a characteristic white spirit odour.	For interior or exterior use. An excellent primer for hard or resinous woods.	<u>Limitations</u>
<u>Finish</u>	<u>Surface Preparation</u>	Oily hardwoods such as teak or iroko must be fully degreased with white spirit or meths prior to the application of the primer. Failure to do this will lead to extended drying time and or adhesion failure.
Matt	Ensure the substrate to be painted is sound and free from any surface contaminant likely to give adhesion problems (e.g. wax, grease etc).	<u>Environmental Info.</u>
<u>Colour(s)</u>	<u>Application Method</u>	
Aluminium	Brush, Roller, Spray Ensure product is <u>thoroughly</u> stirred with a broad stirrer prior to use. Apply one or two full coats.	Paint Product UN No. 1263.
<u>Packaging</u>	<u>Recommended Spreading Rate</u>	
250ml, 500ml, 1litre, 2.5litre. Larger sizes may be available on request dependent on volume required.	13m ² /ltr	Tor Coatings Ltd. Portobello Industrial Est, Birtley Chester-le Street County Durham DH3 2RE
<u>Disclaimer;</u> The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. It is our recommendation that a trial area is first coated to ensure the product is satisfactory to individual requirements	For Technical Enquiries, Material Safety Data Sheets Telephone Sales on 0191 4106611	