

BLACKFRIAR PAINTS LTD

TECHNICAL DATA SHEET

BF0630005 Blackfriar Wood Preservative Goldstar Clear.

Revision date:
01/01/11

<p><u>Product Information</u></p> <p><u>N.B. Read all container instructions prior to use</u></p> <p><u>Description</u></p> <p>A deep penetrating clear wood preservative. HSE No. 8317</p> <p><u>Usage/purpose</u></p> <p>Interior or exterior use. For the preservation of bare (unpainted or varnished) wood prior to painting, staining or varnishing.</p> <p><u>Characteristics</u></p> <p>A thin clear deep penetrating liquid with a characteristic white spirit odour.</p> <p><u>Finish</u></p> <p>Not a finish.</p> <p><u>Colour(s)</u></p> <p>Clear.</p> <p><u>Packaging</u></p> <p>1litre, 2.5litre, 5litre, 25litre. Larger sizes may be available on request dependent on volume required.</p> <p><u>Disclaimer;</u></p> <p>The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. It is our recommendation that a trial area is first coated to ensure the product is satisfactory to individual requirements</p>	<p><u>Technical Spec Composition</u></p> <p>Active ingredients: Dichlofluanid, 3-Iodo-2-Propynyl-N-Butyl Carbamate, and Permethrin in White Spirit</p> <p><u>Properties</u></p> <p>VOC Content: max 765 g/litre.</p> <p><u>Performance</u></p> <p>Deep penetrating. Protects against wet rot, dry rot, blue staining and wood boring insects. Harmless to plant life when dry.</p> <p><u>Surface Preparation</u></p> <p>Ensure the substrate to be treated is sound, clean, dry and free from any surface contaminants.</p> <p><u>Application Method</u></p> <p>Brush, Dipping, Spray, Ensure preserver is thoroughly shaken prior to use. Wood in contact with the ground (i.e. Fence posts) should be soaked in Preservative for a <u>minimum</u> of one hour.</p> <p>For Technical Enquiries and Material Safety Data Sheets Contact Sales on 0191 4106611</p>	<p><u>Recommended Spreading Rate</u></p> <p>4-8m²/ltr depending on the porosity of the wood.</p> <p><u>Thinning</u></p> <p>Do not thin</p> <p><u>Drying Time</u></p> <p>Touch dry in 2-4 hours over-coatable after 24 hours under normal conditions (20°C 50% r/h). Allow Preserver to dry thoroughly before over-coating.</p> <p><u>Cleaning</u></p> <p>Clean application equipment or spills with white spirit or Blackfriar Brush Cleaner</p> <p><u>Limitations</u></p> <p>Absorbent substrates may take longer than 24 hours to dry. Not a finish. <u>Must</u> be over coated.</p> <p><u>Environmental Info.</u></p> <p>Harmful Dangerous for the environment</p> <p>Paint Product UN No. 1263.</p> <p>Tor Coatings Ltd. Portobello Industrial Est, Birtley Chester-le Street County Durham DH3 2RE</p>
---	---	---